

## Rubber (SBR quality) – Technical Data Sheet

### mechanical parameters

Yield stress:	specific 6,7 MPa
Tensile strain at yield:	300 %
Hardness:	95° Shore

### electrical parameters

comparative tracking index	CTI 250
----------------------------	---------

### other parameters

glow wire	960 °C (3,2mm)
-----------	----------------

UV-radiation: not limiting the operation during life time

Contamination free of: cadmium, halogen; silicon